

## SOLO COLOR - 700

Code	Description	Colour Index	Pigment* %	Light** Fastness			Weather** Fastness			Specific* Gravity gm/c <sup>3</sup>	Composition* by Weight %			Resistance**	
				F	M	R	F	M	R		Pigment Solid	Vehicle	Volatile	Alkali	Acid
BS	Blue	PB 15:3	32	8	8	8	5	5	5	1.23	44.68	9.54	45.78	5	5
VS	B.V. Yellow	PY 184	39	7-8	7-8	7-8	4-5	4-5	4-5	1.52	57.91	6.56	35.53	5	5
XS	Bordeaux	PV 19	14	7	7	7	4-5	4	3-4	1.23	39.56	6.73	53.71	5	5
YS	Medium Yellow	PY 74	24	7-8	7-8	6-7	4-5	3-4	3	1.27	50.00	5.33	44.32	5	5
LS	Lemon Yellow	PY 138	19	7	7-8	7-8	4-5	4-5	4	1.35	49.44	6.99	43.57	5	5
MS	Magenta	PR 122	20	7-8	8	7-8	4	4-5	4	1.13	36.78	7.24	55.98	5	5
TS	Black	PBk 7	29	8	8	8	5	5	5	1.27	46.64	7.46	45.90	5	5
OS	Orange Red	PR 168	8	8	8	8	5	5	5	1.41	44.75	5.59	49.66	5	5
AS	Yellow Oxide	PY 42	49	8	8	8	5	5	5	1.75	58.62	5.67	35.71	5	5
DS	Orange Yellow	PY 83	23	7-8	7-8	6-7	4	4	3	1.40	57.08	5.60	37.32	5	5
ES	Red Oxide	PR 101	47	8	8	8	5	5	5	1.69	61.00	7.15	32.02	5	5
RS	Red	PR112	25	7-8	6-7	6	4-5	3	3	1.32	48.00	7.31	44.72	5	5
VS	Violet	PV 23	14	8	7-8	7-8	4-5	4	4	1.32	44.45	6.19	49.36	5	5
GS	Green	PG 7	41	8	8	8	5	5	5	1.44	56.00	4.95	40.00	5	5